

ARMY RESEARCH LABORATORY



Theoretical Evaluation of Moisture Protection Using Coatings

by J. F. Newill, S. H. McKnight, C. P. R. Hoppel,
G. R. Cooper, and M. S. Berman

ARL-TR-2016

July 1999

Approved for public release; distribution is unlimited.

DTIC QUALITY INSPECTED 4

19990819 072

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-2016**July 1999**

Theoretical Evaluation of Moisture Protection Using Coatings

**J. F. Newill, S. H. McKnight, C. P. R. Hoppel, G. R. Cooper,
and M. S. Berman**

Weapons and Materials Research Directorate, ARL

Abstract

A theoretical approach is used to determine important attributes for moisture protection of polymer-matrix composite structures provided by polymeric coatings. Developed solutions are used to evaluate a range of coating materials and thicknesses for thin and thick substrates. The diffusion constants and the saturation levels for the coating material were obtained from the range of available coating materials. The results include typical diffusion patterns for coating materials, saturation of the coating layer, development of moisture through time, and effects of the material properties for the various substrate thicknesses. Moisture diffusion behavior at the substrate-coating interface is also presented. For relatively thick coating layers, the results show that the diffusion constant and the saturation level of the coating must both be low to significantly affect the diffusion process. The study also shows differences in the behavior of the substrate-coating interface.

Table of Contents

	<u>Page</u>
List of Figures	v
List of Tables	vii
1. Introduction	1
2. Kinetics of Fickian Moisture Diffusion	2
3. Relative Humidity and Moisture Saturation	4
4. Methodology	5
5. Typical Results	9
6. Effects of Coating	10
7. Conclusions	17
8. Future Work	18
9. References	19
Distribution List	21
Report Documentation Page	33

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Schematic of Problem Description	6
2. Diffusion Results for a Coated Substrate, $k = 2$, $a = 1$, $L_s = 0.5$ in, and $L_c = 0.01$ in	9
3. Short Time Behavior of the Coating Layer	9
4. Effect of Coatings Shown Though the Diffusion Potential at the Midplane ($L_s = 0.1$ in, $L_c = 0.01$ in)	11
5. Diffusion Potential at the Midplane for $L_s = 0.1$ in and $L_c = 0.001$ in	11
6. Diffusion Potential at the Midplane for $L_s = 0.1$ in and $L_c = 0.002$ in and $L_c = 0.01$ in, Respectively	12
7. Diffusion Potential at the Midplane for $L_s = 0.5$ in and $L_c = 0.002$ in and $L_c = 0.01$ in, Respectively	13
8. Diffusion Potential at the Interface Between the Coating and Substrate	14
9. Effect of a and k at $t = 800$ hr	15
10. Effect of a and k at $t = 10,000$ hr	15
11. Effect of a and k for $L_s = 0.1$ in and $L_c = 0.01$ in for $t = 800$ hr for Small a	16
12. Effect of a and k for a Very Thick Coatings	17

INTENTIONALLY LEFT BLANK.

List of Tables

<u>Table</u>	<u>Page</u>
1. Moisture Saturation Levels for Selected Graphite Fiber-Reinforced Composites	5

INTENTIONALLY LEFT BLANK.

1. Introduction

While most polymers are considered “water proof,” that is only partially true in the context of liquid water flowing through the material. However, it is widely recognized that individual water molecules or clusters can be readily absorbed into polymers via diffusion mechanisms. There have been many studies and theories that relate to polymer structure and moisture diffusion behavior. These works have sought to understand the diffusion process from a fundamental level and have provided insight into the mechanisms for moisture diffusion. These works have also guided appropriate simplifications of the diffusion processes in polymers to enable readily usable models to predict moisture transport. This understanding and predictive capability for moisture diffusion in and through polymers is important in a number of materials applications including polymer-matrix composites.

It is understood that combinations of temperature and high humidity cause problems with the performance of plastics and fiber-reinforced plastics (Pipes, Vinson and Chou 1976, Shen and Springer 1976). Moisture absorption is a significant design consideration for polymer-matrix composites. In composites, water causes weight gain, hygrothermal expansion, and degradation of material properties (Pipes, Vinson, and Chou 1976; VanLandingham, Eduljee, and Gillespie 1995). As moisture diffuses into the polymer, it disrupts the local polymer structure and impacts the physical and mechanical properties of the material. Low levels of water in the polymer can also cause a reduction in the glass transition temperature (T_g) and the elastic modulus of the matrix (McCrum, Buckley, and Bucknall 1988). Semi-empirical models have related the reduction of T_g to the moisture content of the polymer. The reduction in T_g is material dependent but can be a serious consideration in the design of composite structure. Hence, the properties at the “wet T_g ” are often used to determine upper-use temperatures for a given polymer in specific applications and design allowables are frequently derived from mechanical characterization of materials that are fully saturated with moisture. Higher levels of moisture can cause cracks and delaminations to form in the composite and further degrade the performance of the composite structure.

Moisture absorption in complex composite parts is controlled by material properties, geometry, and processing. Material properties and processing affect both the moisture diffusion

rate and the amount of moisture that can be absorbed in the structure. The geometry influences the distribution through the surface area to volume ratio of different parts of the structure where a high surface area to volume will allow saturation to occur at a faster rate. Defects such as voids, microcracks, and pinholes affect the rate by providing a transportation mechanism into the part. These defects are also sites for water clusters to nucleate and hold water in the associated liquid state. These factors must be considered if a predictive capability is to be established for quantifying the moisture content in composite structures.

The theory presented in this paper consists of a method for analyzing moisture diffusion in multidomain structures particularly applicable to composites that have been covered with organic coatings. While diffusion in polymers and polymeric coatings can be defect driven, this paper takes a theoretical approach to characterize the effectiveness of ideal (no cracks or pinholes) coatings on composites. This allows the basic material properties of the coating and substrates, as well as the coating thickness, to be evaluated analytically to focus experimental work on the actual materials and processes. The theoretical work can then be used to extend predictions to complicated structures and realistic long-term environments.

2. Kinetics of Fickian Moisture Diffusion

In general, polymers can absorb moisture from their environment due to the nature of their structure. The degree and rate at which polymers can absorb moisture is very dependent on both the chemical and physical structure of the polymer of interest. Certain polymers are more hygroscopic than others and naturally absorb more moisture. Moisture transport in polymeric materials is related to the solubility of water (in the vapor phase) in the polymer and the moisture diffusion rate at a given temperature. The equilibrium of moisture absorption in polymers can be related to the relative humidity of the environment thermodynamically through Henry's law (Springer 1988; Marsh et al. 1988). The rate of diffusion is often described by Fick's second law and is strongly temperature dependent. However, in certain cases, non-Fickian diffusion is observed and more complicated analysis must be used to describe this behavior. For this work, attention is focused on Fickian diffusion mechanisms and state conditions where this assumption may be assumed.

It is convenient to begin moisture diffusion analysis, assuming Fickian diffusion for the moisture uptake for a single homogenous material. Also, if the sample thickness is much less

than the length and width, the diffusion can be considered to be one-dimensional. In this case, Fick's second law is expressed as

$$\frac{\partial c}{\partial t} = D \frac{\partial^2 c}{\partial x^2} \quad (1)$$

For the case of an initially dry coating of thickness $2l$, and a simple constant concentration boundary conditions at $+l$ and $-l$, there is a well-known solution. This familiar series solution is obtained as

$$\frac{C(z,t)}{C_{\infty}} = 1 - \frac{4}{\pi} \sum_{n=0}^{\infty} \frac{(-1)^n}{(2n+1)} \exp\left[\frac{-D(2n+1)^2 \pi^2 t}{4l^2}\right] \cos\left[\frac{(2n+1)\pi z}{2l}\right] \quad (2)$$

In this equation, C represents the concentration at a given z and t , C_{∞} is the equilibrium concentration, and D is the diffusion constant for water in the coating. The assumptions implicit in this solution are that (1) the coating is uniform in properties and composition and initially free from moisture, (2) the equilibrium moisture concentration at $\pm l$ is achieved instantaneously, and (3) the temperature of the system remains constant.

If equation (2) is integrated over z , the total uptake at any time can be obtained. Here, it is common to normalize the uptake with its ultimate value (Comyn 1992). The fractional uptake is expressed by

$$\frac{M(t)}{M_{\infty}} = 1 - \frac{8}{\pi^2} \sum_{n=0}^{\infty} \frac{1}{(2n+1)^2} \exp\left[\frac{-(2n+1)^2 \pi^2 D t}{4l^2}\right] \quad (3)$$

Often, equation (3) is approximated by neglecting the higher order terms in the infinite series. Ignoring these terms, equation (3) simplifies substantially and the familiar square root relationship between mass uptake vs time is revealed as

$$\frac{M}{M_{\infty}} = \frac{2}{l} \left[\frac{Dt}{\pi} \right]^{1/2} \quad (4)$$

This equation has been widely used to determine diffusion coefficients of permeants in polymers. Several excellent studies on moisture uptake of polymers and composites have been published previously (Comyn 1992; Fieldson and Barbar 1993) that have revealed the usefulness of these techniques. In general, the linear behavior exists up to fractional uptakes of 0.6. Thus,

by monitoring the mass of samples exposed to moisture, the diffusion coefficient of water can be readily obtained. The effect of temperature on the rate of moisture diffusion can also be evaluated by conditioning samples and monitoring weight gain at different temperatures. Generally, an Arrhenius relationship will describe the temperature dependence of moisture diffusivity in polymer and polymer-composite samples.

The Fickian model is generally accepted as a reasonable approximation for diffusion of moisture in graphite epoxy exposed to humid air (Springer 1988). However, significant deviations from Fick's law can occur at high temperatures, when materials are immersed in liquids or when diffusion occurs through cracks or voids in the material (Springer 1988; Cai and Weitsman 1994). Immersion of the composite in liquids reduces the activation energy of diffusion, causing moisture to be absorbed at a higher rate than predicted by equation (1) (Woo and Piggott 1987). Cracks and voids facilitate moisture diffusion by increasing exposed surface area and acting as easy paths for moisture transport. Few studies have quantified the effects of voids and other high-permeability pathways on the amount and rate of moisture absorption. One study (Harper, Staab, and Chen 1987) has indicated that an increase of void-volume fraction from 1% to 5% in a graphite-epoxy laminate increased the moisture diffusion rate and saturation moisture content significantly for a range of humidity levels. Furthermore, as expected, the deviation from Fickian behavior was very large for the 5% void-volume fraction laminate.

3. Relative Humidity and Moisture Saturation

Polymer-matrix composites eventually reach maximum moisture content for a given surrounding humidity level. The relation between the maximum moisture content and the external humidity level is given by

$$M_m = \alpha(R.H.)^\beta, \quad (5)$$

where M_m is the maximum moisture content, α and β are material constants, and $R.H.$ is the surrounding relative humidity level (Tsai 1988). For most composite materials, the constant β has a value close to 1.0. Experimental values of the maximum moisture content for several graphite fiber-reinforced composites are shown in Table 1. The uptake values can vary widely, even for apparently similar material systems. For epoxy resins used as matrix materials, the equilibrium uptake is strongly dependent on the curing agent that is selected for that system. It

has been shown that polar curatives, such as diaminodiphenylsulfone (DDS), tend to cause higher saturation levels than similar curing agents with hydrophobic side groups (Springer 1988). The data on the IM7/K3B graphite fiber-reinforced polyimide was included to show the sensitivity of the matrix saturation level to the surrounding relative humidity. The saturation level of the IM7/K3B increases about 13% when the relative humidity is increased from 97% to 100%. VanLandingham, Eduljee, and Gallespie (1995) have also noted that the saturation level of the composites increases with repeated exposure to moisture. If the composites are saturated with moisture, then dried out and resaturated, they will have an increased maximum moisture content.

Table 1. Moisture Saturation Levels for Selected Graphite Fiber-Reinforced Composites

Material System	Exposure (% R.H.)	Saturation (% Moisture)	Reference
T300/1034	Immersed in Water	1.70	Tsai 1988
AS4/3501-5	Immersed in Water	1.90	Tsai 1988
T300/5208	Immersed in Water	1.50	Tsai 1988
T650-35/F584	98	0.62	Smith et al. 1993
AS4/8553-45	98	0.84	Smith et al. 1993
T650-35/1914-4	98	0.63	Smith et al. 1993
T650-35/1914-6	98	0.66	Smith et al. 1993
IM7/K3B	89	0.43	VanLandingham, Eduljee, and Gallespie (1995)
IM7/K3B	97	0.45	VanLandingham, Eduljee, and Gallespie (1995)
IM7/K3B	100	0.51	VanLandingham, Eduljee, and Gallespie (1995)

4. Methodology

This study investigates theoretical diffusion performance of coated substrates. It is intended to help focus experimental work and provide estimates of the "best case" moisture protection that can be afforded by coatings. As was mentioned before, many practical issues, such as quality of the coating, cracks, processing and application, and defects in the coating and substrate, are not addressed here. Figure 1 shows the schematic of the problem. The problem is divided into two regions: the substrate and the coating. The substrate is the material that is being

protected from moisture intrusion. The purpose of this paper is to investigate some of the geometric parameters and material properties that govern moisture diffusion.




Figure 1. Schematic of Problem Description.

Figure 1 also defines the interface and boundary conditions used for solution. The solution is divided into two domains each with its own local coordinate system. The first domain extends from $x_0 = 0$ to $x_0 = L_s$ and the second domain extends from $x_1 = 0$ at the interface to $x_1 = L_c$ at the outside boundary. It is assumed that both domains start without any moisture. The problem is set up to investigate symmetric one-dimensional loading of the structure. The use of symmetry implies that the midplane boundary condition is represented by zero flux. At the right side of the domain, equation (5) is used where the “ α ” is assumed to be the saturation level of the coating material and “ β ” is assumed to be 1 (Tsai 1988). At the interface a similar condition exists (Carslaw and Jaeger, 1959) two conditions must be met. First, the driving potential of the two materials must be the same:

$$\frac{u}{Sat_s} = \frac{w}{Sat_c}, \text{ or } k u = w, \text{ where } k = \frac{Sat_c}{Sat_s}. \quad (6)$$

The second condition is that the flux at the interface must be continuous:

$$D_s \frac{\partial u}{\partial x_0} = D_c \frac{\partial w}{\partial x_1}. \quad (7)$$

There are two important ratios that are present in this problem. The first, the ratio of the saturation levels, is described in equation (6), and the second is the ratio of the diffusion rates of the coating material and the substrate:

$$a = \frac{D_c}{D_s}. \quad (8)$$

The range of values used for a and k in this study were obtained from reviewing the moisture literature and data from coating manufacturer. The range of diffusion rates for coating materials was from an order of magnitude below the diffusion rate for the substrate (T650/1914, $6.6 \cdot 10^{-6}$ in²/hr) (Bogetti et al. 1997) to an order of magnitude above. The range for the saturation level of the coating materials was from 0.25 times to 8 times the saturation level for the substrate (T650/1914's saturation level is 0.63 %). This does not imply that there is a coating that represents every combination of a and k used in the study. The aim of the study is to find the key material attributes, not to look at particular systems. The next step in this work is to characterize available coating systems for appropriate use in applications.

The system is solved using both exact and numerical solutions, although the results contained in this paper are from the numerical work. The solution was obtained in the following manner.

Finite difference methods (FDMs) change the differential operators to algebraic operators. The algebraic operators are applied over a discretized approximation of the original domain.

The operators used are implicit Crank-Nickolson algebraic operators. Defining the following for convenience (Greenberg, 1978):

$$r_i = \frac{\alpha_i^2 \Delta t}{2\Delta x^2}, \quad (9)$$

and

$$\Delta x_i = \frac{L_i}{ns}, \quad (10)$$

where $i = c$ or s for the coating or substrate layer, respectively. The governing equation is

$$r_k u_{i+1,j+1} - (2r_k - 1)u_{i,j+1} + r_k u_{i-1,j+1} = -r_k u_{i+1,j} + (2r_k - 1)u_{i,j} - r_k u_{i-1,j}. \quad (11)$$

The subscript $k = s$ for $i \in [1, ns - 2]$ and $k = c$ for $i \in [ns + 1, DOF - 2]$, where ns is the number of nodes in the substrate and DOF is the number of degrees of freedom in the system. Note, for convenience, the primary dependant variable in the coating layer, w , has been renamed as u with subscripts from $ns + 1$ to $DOF - 1$. Four additional equations are needed to complete the system. These equations are the boundary conditions and the interface conditions. The boundary conditions are defined in the next two equations:

$$u_{1,j+1} - u_{1,j} - u_{0,j+1} + u_{0,j} = 0 \quad (12)$$

and

$$u_{DOF-1} = \alpha(R.H.)^\beta. \quad (13)$$

The interface conditions are given in the next two equations:

$$k u_{ns,j+1} - u_{ns+1,j+1} = k u_{ns,j} - u_{ns+1,j} \quad (14)$$

and

$$r_s(u_{ns,j+1} - u_{ns-1,j+1}) + r_c(u_{ns+1,j+1} - u_{ns+2,j+1}) = -r_s(u_{ns,j} - u_{ns-1,j}) - r_c(u_{ns+1,j} - u_{ns+2,j}). \quad (15)$$

This leaves a fully defined system of the following form,

$$\mathbf{A} \mathbf{u}^{new} = \mathbf{B} \mathbf{u}^{old} + \mathbf{c}, \quad (16)$$

which is easily solved and iterated for the appropriate time:

$$\mathbf{u}^{new} = \mathbf{A}^{-1} \mathbf{B} \mathbf{u}^{old} + \mathbf{A}^{-1} \mathbf{C}. \quad (17)$$

5. Typical Results

Figure 2 and Figure 3 show typical results for coated substrates.




Figure 2. Diffusion Results for a Coated Substrate, $k = 2$, $a = 1$, $L_s = 0.5$ in, and $L_c = 0.01$ in.




Figure 3. Short Time Behavior of the Coating Layer.

As seen in Figure 2, there are several important features. First, at the interface between the coating and substrate, there is a discontinuity. The discontinuity is a function of the difference in the saturation levels of the coating and substrate. Although, it is difficult to see in

the figure, the flux at the interface is also matched. The development of the solution in the substrate is very similar to the solution in a noncoated layer.

Figure 3 shows that at 30 hr, the coating layer appears to have assumed a quasi-static solution and is almost fully saturated. This implies that any additional moisture entering the coating layer is being transferred to the substrate. It also implies that the material properties of the coating layer should dominate the diffusion process. It is seen in later figures that this is not always the case.

6. Effects of Coating

The next series of figures investigates the effect of the coating thickness and relative materials properties for a thin ($L_s = 0.1$ in) and thick ($L_s = 0.5$ in) substrates. In order to look at moisture penetration into the substrates, the normalized moisture level at the midplane of the substrate was used as a measure. The moisture level was normalized by dividing by the saturation level of substrate and is referred to as the diffusion potential. As a comparison, the equivalent substrate without a coating is shown to gauge relative diffusion performance. The substrate with $a = 1$ and $k = 1$ implies that the coating layer has the same diffusion rate and saturation level as the substrate. For each of the analysis, material properties were chosen for the substrate, then the coating material properties were varied relative to the substrates.

Three types of figures are needed in order to assess the diffusion performance of a coating, time histories, substrate-coating interface plots, and diffusion potential vs the material property ratios' a and k . The time histories show deviation during the diffusion process and ensure that relative comparisons are accomplished at appropriate times. The substrate-coating interface plots provide insight into how the coating works, and the diffusion potential vs material property ratios help isolate effective ranges for the material attributes. On each of the graphs, the diffusion performance for several combinations of the ratios a and k are given to gauge the relative diffusion performance.

Figure 4 shows the general effects of coatings. Since each line in the figure represents a different type of coating, the separations between the lines imply the particular coatings effect.

Each of the lines should be gauged against the case where a and k are equal to 1, which represents the effect of just thickening the substrate without adding a coating.




Figure 4. Effect of Coatings shown though the Diffusion Potential at the Midplane ($L_s = 0.1$ in, $L_c = 0.01$ in).

To assess the effectiveness of a coating, the assessment should be made at a time corresponding to the separation near the largest deviation seen in the figure. Figure 5 and Figure 6 show the diffusion potential performance for three different coating thickness on a relatively thin substrate ($L_s = 0.1$ in).




Figure 5. Diffusion Potential at the Midplane for $L_s = 0.1$ in and $L_c = 0.001$ in.




Figure 6. Diffusion Potential at the Midplane for $L_s = 0.1$ in and $L_c = 0.002$ in and $L_c = 0.01$ in, respectively.

Figure 5 shows relative short time (800 hr ~ 1 month) performance of the substrate. The figure shows that, at 800 hr, the diffusion potential is around 0.66, where a value of 1 represents the saturation value. It is very interesting to see that the wide range of material properties does not have any appreciable effect on the diffusion. Figure 6 shows the same results for a coating thickness that is twice as thick ($L_c = 0.002$ in) and ten times as thick ($L_c = 0.01$ in). In this figure, some very small differences can be seen around 800 hr. The maximum value remains near 0.66, and it is important to note that the coated substrates do not appreciably perform differently than the uncoated substrates. In Figure 6, with $L_c = 0.01$ in, a dramatic difference can be seen in the diffusion performance of the different coatings. Even with this relatively thick coating, five of the nine combinations of a and k do not cause the coated substrate to behave differently from the uncoated substrate. The figure shows, that if the material properties of the coating are chosen properly and the coating is applied thick enough, potentially the diffusion can be cut in half. It appears from these figures that control of both a and k are necessary to affect diffusion. This is not surprising as the total permeability of the coating can be expected to be a product of the diffusivity and solution of moisture in the coating. It is also interesting to note that some of the time-history lines cross. This implies that the diffusion rate and saturation level have different effects for short and long time periods.

Figure 7 shows the effects of the same coatings on a thick substrate. The $L_c = 0.001$ in case was omitted since very little diffusion difference is seen in the thicker coatings. As is seen in the figures, for thick substrates, the coatings have very little effect on the moisture diffusion. Only in the case where the coating is 0.01 in thick is there any difference in performance and the performance difference is negligible.




Figure 7. Diffusion Potential at the Midplane for $L_s = 0.5$ in and $L_c = 0.002$ in and $L_c = 0.01$ in, Respectively.

Figure 8 shows the time history of moisture at the interface between the coating and the substrate. The figure shows that, for many of the combinations of coatings, the interface goes to the saturation level very quickly. Again, many of the lines cross each other showing that the saturation level and the diffusion rate operate on different time scales. Finally, the figure also shows that, in order to affect the diffusion rate in the substrate, the interface should not quickly drive to the saturation level of the coating materials. When the saturation level is reached, the maximum amount of moisture is diffusing from the coating into the substrate. If a lower diffusion potential can be held, allowing a smaller amount of moisture to be transferred. This appears to be an effective coating attribute. Later, Figure 9 and Figure 10 directly address combinations of a and k , which offer the best protection.




Figure 8. Diffusion Potential at the Interface Between the Coating and Substrate.

Looking at the interface performance for $L_c = 0.01$ in, again there appears to be very little difference in the various coatings. In each case, the diffusion potential very quickly goes to the saturation level of the materials. When compared to the thin substrate results, one of the main differences is that the a and k combinations offering some protection did not saturate quickly and that behavior is absent here. Again, some of the lines cross each other, which implies that the time scales are different for the diffusion rate and saturation levels.

It should also be noted that in Figure 8, some of the lines imply that, with the wrong combination of coating material properties, moisture can be absorbed faster in the substrate than the substrate without a coating.

Figure 9 and Figure 10 investigate the relationships between a , k , and the midplane diffusion potential for various thicknesses of coatings and substrates. These figures, with the exception of Figure 9, show that the coating material properties have very little effect on the amount of moisture uptake in the substrate. For the different material properties, the curves remain flat with very little difference for the midplane diffusion levels. Only when the diffusion rate is very low is the diffusion behavior changing. Figure 9 shows more divergent behavior.




Figure 9. Effect of a and k at $t = 800$ hr.




Figure 10. Effect of a and k at $t = 10000$ hr.

Figure 11 shows a portion of Figure 9 for small values of a .




Figure 11. Effect of a and k for $L_s = 0.1$ in and $L_c = 0.01$ in for $t = 800$ hr for Small a .

Figure 11 shows significant reduction in moisture uptake for small values of a . This translates into a diffusion coefficient for the coating around an order of magnitude smaller than the diffusion coefficient for the substrate. It is also clearly shown in this figure that, if the saturation value for the coefficient for the coating is relatively much higher than the saturation value for the substrate, the coating will facilitate moisture uptake in the substrate. This is seen when comparing the curve for $a = 1$ and $k = 1$ to the other curves. It is also seen that this effect can be counteracted by lowering the diffusion coefficient.

Figure 12 shows interface results for a thick coatings ($L_c = 0.05$ in) on a very thin substrate ($L_s = 0.05$ in) and a thick substrate ($L_s = 0.5$ in). In both cases with the right combinations of a and k , the coating are effective. On the thin substrate, similar values to earlier cases for a and k are again effective. For the thick substrate, now that the coating thickness is approach 10%, with the proper values for a and k the coating is protecting the substrate.




Figure 12. Effect of a and k for a Very Thick Coatings.

7. Conclusions

Polymeric coatings can be used to reduce the moisture absorption in polymer and polymer-composite structures. The analytical approach taken in this paper demonstrates that the thickness, diffusion constant, and saturation level of the coating relative to those of the substrate are essential to the coatings effectiveness. The diffusion rate and the saturation level of the coating must both be very small compared to the substrate for the coating to affect the long-term diffusion behavior. Even when the material constants are optimized, the coating must be relatively thick to affect a substantial reduction of moisture absorption. For the substrates studied in this paper, the thickness of the coating needed to be 10% of the thickness of the substrate to achieve effective protection. Even with coatings 10% of the substrate thickness, many values of a and k are not effective in protecting the structure from moisture ingress. This is partially due to the speed that the coating layer achieves a quasi-steady-state distribution. The coatings that did not saturate quickly were more effective at protecting moisture diffusion. This is not to say that an impermeable coating is the best solution, since it also does not allow

moisture to exit the substrate and could consequently cumulate moisture. This will be investigated in future studies that address temperature effects and fluctuating environmental conditions. It is also interesting to note that the saturation level of the coating and the diffusion rate of the coating can act on different time scales. The results from this study will be used to target the important attributes to allow the selection of appropriate coatings. Experimental evaluation of the coating and the manufacturing process are necessary to ensure that the chosen system can be implemented effectively in a structure.

8. Future Work

Analytical and numerical solutions for moisture performance of coated substrates have been developed. These solutions are being used to develop methods for approximating coating for large complicated models. In addition, these methods are being compared to different coating system to assess the theoretical performance against coatings that are not “perfect” and contain voids, cracks, other defects, or processing differences. The theories developed will be modified to allow realistic prediction of complicated structures protected by coatings with defects.

9. References

- Bogetti T. A., C. P. R. Hoppel, J. F. Newill, J. Elwood, and J. W. Gillespie, Jr. "Moisture Diffusion in a Graphite-Epoxy Composite." *Proceedings of the American Society for Composites Twelfth Technical Conference*, pp. 1133-1140, American Society for Composites, 1997.
- Cai, L. W., and Y. Weitsman. "Non-Fickian Moisture Diffusion in Polymeric Composites." *Journal of Composite Materials*, vol. 28, no.2, pp. 130-154, 1994.
- Carslaw, H. S. and J. C. Jaeger. *Condition of Heat in Solid*. Clarendon Press, Oxford, UK 1959.
- Comyn, J. "Kinetics and Mechanism of Environmental Attack. Silanes and other Coupling Agents." K. L. Mittal, Ed., VSP BV, Zeist, Netherlands, 1992.
- Fieldson, G. T., and T. A. Barbari. "The Use of FTi.r.-a.t.r. Spectroscopy to Characterize Penetrant Diffusion in Polymers." *Polymer*, 34 (6) pp 1146-1156, 1993
- Greenberg, M. D., *Foundations of Applied Mathematics*. Prentice-Hall, Englewood Cliffs, NJ, 1978.
- Harper B. D., G. H. Staab, and R. S. Chen. "A Note on the Effects of Voids Upon the Hygral and Mechanical Properties of AS4/3502 Graphite/Epoxy." *Journal of Composite Materials*, vol. 21, p. 280, March 1987.
- Marsh, L. L., R. Lasky, D. P. Seraphim, and G. S. Springer. "Moisture Solubility and Diffusion in Epoxy and Epoxy-Glass Composites." *Environmental Effects on Composite Materials; Volume 3*, G. S. Springer (editor), Technomic (1988).
- McCrum, N. G., C. P. Buckley, and C. B. Bucknall. *Principles of Polymer Engineering*. Oxford University Press, NY, 1988.
- Pipes R. B., J. R. Vinson, R. B., and T. W. Chou. "On the Hygrothermal Response of Laminated Composite Systems." *Journal of Composite Materials*, vol. 10, pp. 129-148, April 1976.
- Shen, C. H., and G. S. Springer. "Moisture Absorption and Desorption of Composite Materials." *Journal of Composite Materials*, vol. 10, pp. 5-20, January 1976.

- Smith, M. T., G. L. VanArsdale, M. J. Riess, L. R. Shotwell. G. R. Lakshminarayanan, and E. L. Logsdon. "Evaluation of Environmental Conditioning Effects on Composite Material Systems." ARAED-CR-93001, U.S. Army Armament Research, Development and Engineering Center, Picatinny Arsenal, NJ August 1993.
- Springer, G. S. "Moisture Content of Composites Under Transient Conditions." *Journal of Composite Materials*, vol 11, p. 107, January 1977.
- Springer, G. S. "Environmental Effects." *Composites Design, 4th Edition*, S. W. Tsai (editor), Think Composites Dayton, OH, 1988.
- Tsai, S. W. *Composites Design, 4th Edition*. Think Composites, Dayton, OH, 1988.
- VanLandingham, M. R., R. F. Eduljee, and J. W. Gillespie, Jr. "Hygrothermal Effects on the Material Properties and Behavior of Thermoplastic Polyimide Composites." *Proceedings of the American Society for Composites Tenth Technical Conference*, pp. 525-536, Technomic, 1995.
- Woo, M., and M. R. Piggott. "Water Absorption of Resins and Composites: I. Epoxy Homopolymers and Copolymers." *Journal of Composites Technology & Research*, vol. 9, no. 3, pp. 101-107, 1987.

NO. OF
COPIES ORGANIZATION

2 DEFENSE TECHNICAL
INFORMATION CENTER
DTIC DDA
8725 JOHN J KINGMAN RD
STE 0944
FT BELVOIR VA 22060-6218

1 HQDA
DAMO FDQ
D SCHMIDT
400 ARMY PENTAGON
WASHINGTON DC 20310-0460

1 OSD
OUSD(A&T)/ODDDR&E(R)
R J TREW
THE PENTAGON
WASHINGTON DC 20301-7100

1 DPTY CG FOR RDE HQ
US ARMY MATERIEL CMD
AMCRD
MG CALDWELL
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 INST FOR ADVNCD TCHNLGY
THE UNIV OF TEXAS AT AUSTIN
PO BOX 202797
AUSTIN TX 78720-2797

1 DARPA
B KASPAR
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 NAVAL SURFACE WARFARE CTR
CODE B07 J PENNELLA
17320 DAHLGREN RD
BLDG 1470 RM 1101
DAHLGREN VA 22448-5100

1 US MILITARY ACADEMY
MATH SCI CTR OF EXCELLENCE
DEPT OF MATHEMATICAL SCI
MAJ M D PHILLIPS
THAYER HALL
WEST POINT NY 10996-1786

NO. OF
COPIES ORGANIZATION

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL DD
J J ROCCHIO
2800 POWDER MILL RD
ADELPHI MD 20783-1145

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CS AS (RECORDS MGMT)
2800 POWDER MILL RD
ADELPHI MD 20783-1145

3 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI LL
2800 POWDER MILL RD
ADELPHI MD 20783-1145

ABERDEEN PROVING GROUND

4 DIR USARL
AMSRL CI LP (305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CP CA D SNIDER 2800 POWDER MILL RD ADELPHI MD 20783
1	COMMANDER US ARMY ARDEC AMSTA AR FSE T GORA PICATINNY ARSENAL NJ 07806-5000
3	COMMANDER US ARMY ARDEC AMSTA AR TD PICATINNY ARSENAL NJ 07806-5000
5	US ARMY TACOM AMSTA JSK S GOODMAN J FLORENCE AMSTA TR D B RAJU L HINOJOSA D OSTBERG WARREN MI 48397-5000
5	PM SADARM SFAE GCSS-SD COL B ELLIS M DEVINE W DEMASSI J PRITCHARD S HROWNAK PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC F MCLAUGHLIN PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
4	COMMANDER US ARMY ARDEC AMSTA AR CCH S MUSALLI R CARR M LUCIANO T LOUCEIRO PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR E FENNELL PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR CCH PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR CCH P J LUTZ PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSF T C LIVECCHIA PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR QAC T/C C PATEL PICATINNY ARSENAL NJ 07806-5000

NO. OF
COPIES ORGANIZATION

2 COMMANDER
US ARMY ARDEC
AMSTA AR M
D DEMELLA
F DIORIO
PICATINNY ARSENAL NJ
07806-5000

3 COMMANDER
US ARMY ARDEC
AMSTA AR FSA
A WARNASH
B MACHAK
M CHIEFA
PICATINNY ARSENAL NJ
07806-5000

1 COMMANDER
SMCWV QAE Q B VANINA
BLDG 44 WATERVLIET ARSENAL
WATERVLIET NY 12189-4050

1 COMMANDER
SMCWV SPM T MCCLOSKEY
BLDG 253 WATERVLIET ARSENAL
WATERVLIET NY 12189-4050

8 DIRECTOR
BENET LABORATORIES
AMSTA AR CCB
J KEANE
J BATTAGLIA
J VASILAKIS
G FFIAR
V MONTVORI
G DANDREA
R HASENBEIN
AMSTA AR CCB R S SOPOK
WATERVLIET NY 12189

1 COMMANDER
WATERVLIET ARSENAL
SMCWV QA QS K INSCO
WATERVLIET NY 12189-4050

1 COMMANDER
US ARMY ARDEC
AMSMC PBM K
PICATINNY ARSENAL NJ
07806-5000

NO. OF
COPIES ORGANIZATION

1 COMMANDER
US ARMY BELVOIR RD&E CTR
STRBE JBC
FT BELVOIR VA 22060-5606

2 COMMANDER
US ARMY ARDEC
AMSTA AR FSP G
M SCHIKSNIS
D CARLUCCI
PICATINNY ARSENAL NJ
07806-5000

1 US ARMY COLD REGIONS RSRCH &
ENGNRNG LABORATORY
P DUTTA
72 LYME RD
HANOVER NH 03755

1 DIRECTOR
US ARMY RESEARCH LABORATORY
AMSRL WT L D WOODBURY
2800 POWDER MILL RD
ADELPHI MD 20783-1145

3 COMMANDER
US ARMY MISSILE COMMAND
AMSMI RD W MCCORKLE
AMSMI RD ST P DOYLE
AMSMI RD ST CN T VANDIVER
REDSTONE ARSENAL AL 35898-5247

2 US ARMY RESEARCH OFFICE
A CROWSON
J CHANDRA
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

3 US ARMY RESEARCH OFFICE
ENGINEERING SCIENCES DIV
R SINGLETON
G ANDERSON
K IYER
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

NO. OF
COPIES ORGANIZATION

5 PM
TMA
SFAE GSSC TMA
COL PAWLICKI
K KIMKER
E KOPACZ
R ROESER
B DORCY
PICATINNY ARSENAL NJ
07806-5000

1 PM
TMA
SFAE GSSC TMA SMD
R KOWALSKI
PICATINNY ARSENAL NJ
07806-5000

2 PEO FIELD ARTILLERY SYSTEMS
SFAE FAS PM
H GOLDMAN
T MCWILLIAMS
PICATINNY ARSENAL NJ
07806-5000

2 PM CRUSADER
G DELCOCO
J SHIELDS
PICATINNY ARSENAL NJ
07806-5000

2 NASA LANGLEY RESEARCH CTR
MS 266
AMSRL VS
W ELBER
F BARTLETT JR
HAMPTON VA 23681-0001

2 COMMANDER
DARPA
J KELLY
B WILCOX
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

NO. OF
COPIES ORGANIZATION

6 COMMANDER
WRIGHT PATTERSON AIR FORCE
BASE
WL FIV A MAYER
WL MLBM
S DONALDSON
T BENSON-TOLLE
C BROWNING
J MCCOY
F ABRAHAM
2941 P STREET STE 1
DAYTON OH 45433

1 NSWC
DAHLGREN DIV
CODE G06
DAHLGREN VA 22448

1 NAVAL RESEARCH LABORATORY
CODE 6383
I WOLOCK
WASHINGTON DC 20375-5000

1 OFFICE OF NAVAL RESEARCH
MECH DIV CODE 1132SM
YAPA RAJAPAKSE
ARLINGTON VA 22217

1 NSWC
CRANE DIV
M JOHNSON
CODE 20H4
LOUISVILLE KY 40214-5245

1 DAVID TAYLOR RESEARCH CTR
SHIP STRUCTURES & PROTECTION
DEPARTMENT
J CORRADO CODE 1702
BETHESDA MD 20084

2 DAVID TAYLOR RESEARCH CTR
R ROCKWELL
W PHYLLAIER
BETHESDA MD 20054-5000

1 DEFENSE SPECIAL WEAPONS AGENCY
INNOVATIVE CONCEPTS DIV
R ROHR
6801 TELEGRAPH RD
ALEXANDRIA VA 22310-3398

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	F SHOUP EXPEDITIONARY WARFARE DIV N85 2000 NAVY PENTAGON WASHINGTON DC 0350-2000
1	OFFICE OF NAVAL RESEARCH D SIEGEL 351 800 N QUINCY ST ARLINGTON VA 22217-5660
1	NSWC J H FRANCIS CODE G30 DAHLGREN VA 2448
2	NSWC CODE G32 D WILSON CODE G32 R D COOPER DAHLGREN VA 22448
4	NSWC CODE G33 J FRAYSSE CODE G33 E ROWE CODE G33 T DURAN CODE G33 L D SIMONE DAHLGREN VA 22448
1	CDR, NAVAL SEA SYS CMD D LIESE 2531 JEFFERSON DAVIS HWY ARLINGTON VA 22242-5160
1	NSW M E LACY CODE B02 17320 DAHLGREN RD DAHLGREN VA 22448
1	NSW TECH LIBRARY CODE 323 17320 DAHLGREN RD DAHLGREN VA 22448
4	DIRECTOR LAWRENCE LIVERMORE NATL LAB R CHRISTENSEN S DETERESA F MAGNESS M FINGER PO BOX 808 LIVERMORE CA 94550

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	LOS ALAMOS NATL LAB F ADDESSIO MS B216 PO BOX 1633 LOS ALAMOS NM 87545
1	LOS ALAMOS NATL LAB J REPPA MS F668 PO BOX 1663 LOS ALAMOS NM 87545
1	OAK RIDGE NATL LAB R M DAVIS PO BOX 2008 OAK RIDGE TN 37831-6195
1	PENN STATE UNIV C BAKIS 227 N HAMMOND UNIVERSITY PARK PA 16802
3	UDLP 4800 EAST RIVER RD P JANKE MS170 T GIOVANETTI MS236 B VAN WYK MS389 MINNEAPOLIS MN 55421-1498
4	DIRECTOR SANDIA NATL LAB APPLIED MECHANICS DEPT DIV 8241 W KAWAHARA K PERANO D DAWSON P NIELAN PO BOX 969 LIVERMORE CA 94550-0096
1	DREXEL UNIV A S D WANG 32ND AND CHESTNUT STREETS PHILADELPHIA PA 19104
1	BATTELLE C R HARGREAVES 505 KING AVE COLUMBUS OH 43201-2681

NO. OF
COPIES ORGANIZATION

1 PACIFIC NORTHWEST LAB
M SMITH
PO BOX 999
RICHLAND WA 99352

1 LAWRENCE LIVERMORE NATL LAB
M MURPHY
PO BOX 808 L 282
LIVERMORE CA 94550

1 NORTH CAROLINA STATE UNIV
CIVIL ENGINEERING DEPT
W RASDORF
PO BOX 7908
RALEIGH NC 27696-7908

1 PENN STATE UNIV
R MCNITT
227 HAMMOND BLDG
UNIVERSITY PARK PA 16802

1 PENN STATE UNIV
R S ENGEL
245 HAMMOND BLDG
UNIVERSITY PARK PA 16801

1 PURDUE UNIV
SCHOOL OF AERO & ASTRO
C T SUN
W LAFAYETTE IN 47907-1282

1 STANFORD UNIV
DEPT OF AERONAUTICS AND
AEROBALLISTICS DURANT BLDG
S TSAI
STANFORD CA 94305

1 UCLA, MANE DEPT ENGR IV
H T HAHN
LOS ANGELES CA 90024-1597

2 U OF DAYTON RSRCH INSTITUTE
R Y KIM
A K ROY
300 COLLEGE PARK AVE
DAYTON OH 45469-0168

NO. OF
COPIES ORGANIZATION

1 UNIV OF DAYTON
J M WHITNEY
COLLEGE PARK AVE
DAYTON OH 45469-0240

2 UNIV OF DELAWARE
CTR FOR COMPOSITE MATERIALS
J GILLESPIE
M SANTARE
201 SPENCER LABORATORY
NEWARK DE 19716

1 UNIV OF ILLINOIS AT URBANA
CHAMPAIGN NATL CTR FOR COMPOSITE
MATERIALS RESEARCH
216 TALBOT LABORATORY
J ECONOMY
104 S WRIGHT STREET
URBANA IL 61801

1 UNIV OF KENTUCKY
L PENN
763 ANDERSON HALL
LEXINGTON KY 40506-0046

1 UNIV OF UTAH
DEPT OF MECH & INDUSTRIAL ENGR
S SWANSON
SALT LAKE CITY UT 84112

2 THE UNIV OF TEXAS AT AUSTIN
CENTER FOR ELECTROMECHANICS
A WALLS
J KITZMILLER
10100 BURNET RD
AUSTIN TX 78758-4497

3 VA POLYTECHNICAL INSTITUTE
& STATE UNIV
DEPT OF ESM
M W HYER
K REIFSNIDER
R JONES
BLACKSBURG VA 24061-0219

1 UNIV OF MARYLAND
DEPT OF AEROSPACE ENGINEERING
A J VIZZINI
COLLEGE PARK MD 20742

NO. OF
COPIES ORGANIZATION

1 AAI CORPORATION
T G STASTNY
PO BOX 126
HUNT VALLEY MD 21030-0126

1 J HEBERT
PO BOX 1072
HUNT VALLEY MD 21030-0126

1 ARMTEC DEFENSE PRODUCTS
S DYER
85 901 AVE 53
PO BOX 848
COACHELLA CA 92236

2 ADVANCED COMPOSITE MATERIALS
CORPORATION
P HOOD
J RHODES
1525 S BUNCOMBE RD
GREER SC 29651-9208

1 SAIC
D DAKIN
2200 POWELL ST STE 1090
EMERYVILLE CA 94608

1 SAIC
M PALMER
2109 AIR PARK RD S E
ALBUQUERQUE NM 87106

1 SAIC
R ACEBAL
1225 JOHNSON FERRY RD STE 100
MARIETTA GA 30068

1 SAIC
G CHRYSSOMALLIS
3800 W 80TH STREET
STE 1090
BLOOMINGTON MN 55431

NO. OF
COPIES ORGANIZATION

6 ALLIANT TECHSYSTEMS INC.
C CANDLAND
R BECKER
L LEE
R LONG
D KAMDAR
G KASSUELKE
600 2ND ST NE
HOPKINS MN 55343-8367

1 AMOCO PERF PRODUCTS INC
M MICHNO JR
4500 MCGINNIS FERRY RD
ALPHARETTA GA 30202-3944

1 APPLIED COMPOSITES
W GRISCH
333 NORTH SIXTH ST
ST CHARLES IL 60174

1 BRUNSWICK DEFENSE
T HARRIS
STE 410
1745 JEFFERSON DAVIS HWY
ARLINGTON VA 22202

1 PROJECTILE TECHNOLOGY INC
515 GILES ST
HAVRE DE GRACE MD 21078

1 CUSTOM ANALYTICAL ENGR
SYS INC
A ALEXANDER
13000 TENSOR LANE NE
FLINTSTONE MD 21530

1 NOESIS INC
A BOUTZ
1110 N GLEBE RD STE 250
ARLINGTON VA 22201-4795

1 ARROW TECH ASSO
1233 SHELburne RD STE D 8
SOUTH BURLINGTON VT 05403-7700

1 NSWC
R HUBBARD G33-C
DAHLGREN DIV
DAHLGREN VA 2248-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
5	GEN CORP AEROJET D PILLASCH T COULTER C FLYNN D RUBAREZUL M GREINER 1100 WEST HOLLYVALE ST AZUSA CA 91702-0296
7	CIVIL ENGR RSRCH FOUNDATION H BERNSTEIN (PRESIDENT) C MAGNELL K ALMOND R BELLE M WILLETT E DELO B MATTES 1015 15TH ST NW STE 600 WASHINGTON DC 20005
1	NATL INSTITUTE OF STANDARD AND TECHNOLOGY STRUCTURE & MECHANICS GROUP POLYMER DIV POLYMERS RM A209 GREGORY MCKENNA GAITHERSBURG MD 20899
1	DUPONT CO COMPOSITES ARAMID FIBERS S BORLESKE (DEVELOPMENT MGR) CHESNUT RUN PLAZA PO BOX 80702 WILMINGTON DE 19880-0702
1	GENERAL DYNAMICS LAND SYSTEMS DIV D BARTLE PO BOX 1901 WARREN MI 48090
3	HERCULES INC R BOE F POLICELLI J POESCH PO BOX 98 MAGNA UT 84044

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	HERCULES INC G KUEBELER J VERMEYCHUK B MANDERVILLE JR HERCULES PLAZA WILMINGTON DE 19894
1	HEXCEL M SHELENDICH 11555 DUBLIN BLVD PO BOX 2312 DUBLIN CA 94568-0705
4	INSTITUTE FOR ADVANCED TECH H FAIR P SULLIVAN W REINECKE I MCNAB 4030 2 W BRAKER LN AUSTIN TX 78759
1	INTEGRATED COMPOSITE TECH H PERKINSON JR PO BOX 397 YORK NEW SALEM PA 17371-0397
1	INTERFEROMETRICS INC R LARRIVA (VICE PRESIDENT) 8150 LEESBURG PIKE VIENNA VA 22100
1	AEROSPACE RES & DEV (ASRDD) CORP D ELDER PO BOX 49472 COLORADO SPRINGS CO 80949-9472
1	PM ADVANCED CONCEPTS LORAL VOUGHT SYSTEMS J TAYLOR PO BOX 650003 MS WT 21 DALLAS TX 76265-0003
2	LORAL VOUGHT SYSTEMS G JACKSON K COOK 1701 W MARSHALL DR GRAND PRAIRIE TX 75051

NO. OF
COPIES ORGANIZATION

1 BRIGS CO
J BACKOFEN
2668 PETERBOROUGH ST
HERDON VA 22071-2443

1 SOUTHWEST RSRCH INSTITUTE
ENGR & MATERIAL SCIENCES DIV
J RIEGEL
6220 CULEBRA RD
PO DRAWER 28510
SAN ANTONIO TX 78228-0510

1 ZERNOW TECHNICAL SERVICES
L ZERNOW
425 W BONITA AVE STE 208
SAN DIMAS CA 91773

1 R EICHELBERGER (CONSULTANT)
409 W CATHERINE ST
BEL AIR MD 21014-3613

1 DYNA EAST CORP
PEI CHI CHOU
3201 ARCH ST
PHILADELPHIA PA 19104-2711

2 MARTIN MARIETTA CORP
P DEWAR
L SPONAR
230 EAST GODDARD BLVD
KING OF PRUSSIA PA 19406

2 OLIN CORP
FLINCHBAUGH DIV
E STEINER
B STEWART
PO BOX 127
RED LION PA 17356

1 OLIN CORP
L WHITMORE
10101 9TH ST NORTH
ST PETERSBURG FL 33702

1 RENNSAELER POLYTECHNIC INST
R B PIPES
PRESIDENT OFC
PITTSBURGH BLDG
TROY NY 12180-3590

NO. OF
COPIES ORGANIZATION

1 SPARTA INC
J GLATZ
9455 TOWNE CTR DRIVE
SAN DIEGO CA 92121-1964

2 UNITED DEFENSE LP
P PARA
G THOMAS
1107 COLEMAN AVE BOX 367
SAN JOSE CA 95103

1 MARINE CORPS SYSTEMS CMD
PM GROUND WPNS
COL R OWEN
2083 BARNETT AVE STE 315
QUANTICO VA 22134-5000

1 OFFICE OF NAVAL RES
J KELLY
800 NORTH QUINCEY ST
ARLINGTON VA 22217-5000

2 NSWC
CARDEROCK DIV
R CRANE CODE 2802
C WILLIAMS CODE 6553
3A LEGGETT CIR
ANNAPOLIS MD 21402

5 SIKORSKY
H BUTTS
T CARSTENSAN
B KAY
S GARBO
J ADELMANN
6900 MAIN ST
PO BOX 9729
STRATFORD CT 06601-1381

1 U WYOMING
D ADAMS
PO BOX 3295
LARAMIE WY 82071

1 MICHIGAN STATE UNIV
R AVERILL
3515 EB MSM DEPT
EAST LANSING MI 48824-1226

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	AMOCO POLYMERS J BANISAUKAS 4500 MCGINNIS FERRY RD ALPHARETTA GA 30005
1	HEXCEL T BITZER 11711 DUBLIN BLVD DUBLIN CA 94568
1	BOEING R BOHLMANN PO BOX 516 MC 5021322 ST LOUIS MO 63166-0516
1	NAVSEA OJRI G CAMPONESCHI 2351 JEFFERSON DAVIS HWY ARLINGTON VA 22242-5160
1	LOCKHEED MARTIN R FIELDS 1195 IRWIN CT WINTER SPRINGS FL 32708
1	USAF WL/MLSM OL A HAKIM 5225 BAILEY LOOP 243E MCCLELLAN AFB CA 55552
1	PRATT & WHITNEY D HAMBRICK 400 MAIN ST MS 114-37 EAST HARTFORD CT 06108
1	BOEING DOUGLAS PRODUCTS DIV L J HART-SMITH 3855 LAKEWOOD BLVD D800-0019 LONG BEACH CA 90846-0001
1	MIT P LAGACE 77 MASS AVE CAMBRIDGE MA 01887

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	NASA-LANGLEY J MASTERS MS 389 HAMPTON VA 23662-5225
1	CYTEC M LIN 1440 N KRAEMER BLVD ANAHEIM CA 92806
2	BOEING ROTORCRAFT P MINGURT P HANDEL 800 B PUTNAM BLVD WALLINGFORD PA 19086
2	FAA TECH CENTER D OPLINGER AAR-431 P SHYPRYKEVICH AAR-431 ATLANTIC CITY NJ 08405
1	NASA-LANGLEY RC CC POE MS 188E NEWPORT NEWS VA 23608
1	LOCKHEED-MARTIN S REEVE 8650 COBB DR D/73-62 MZ 0648 MARIETTA GA 30063-0648
1	WL MLBC E SHINN 2941 PST STE 1 WRIGHT PAT AFB OH 45433-7750
2	IIT RESERACH CTR D ROSE 201 MILL ST ROME NY 13440-6916
1	MATERIALS SCIENCES CORP B W ROSEN 500 OFFICE CTR DR STE 250 FT WASHINGTON PA 19034
1	DOW-UT S TIDRICK 15 STERLING DR WALLINGFORD CT 06492

NO. OF
COPIES ORGANIZATION

3 TUSKEGEE UNIV
MATERIALS RSRCH LAB
SCHOOL OF ENGR & ARCH
S JEELANI
H MAHFUZ
U VAIDYA
TUSKEGEE, AL 36088

4 NIST
R PARNAS
J DUNKERS
M VANLANDINGHAM
D HUNSTON
POLYMERS DIV
GAITHERSBURG MD 20899

2 NORTHROP GRUMMAN
ENVIRONMENTAL PROGRAMS
R OSTERMAN
8900 E WASHINGTON BLVD
PICO RIVERA CA 90660

1 OAK RIDGE NATL LAB
A WERESZCZAK
BLDG 4515 MS 6069
PO BOX 2008
OAKRIDGE TN 37831-6064

1 CDR USARDEC
T SACHAR
INDUSTRIAL ECOLOGY CTR
BLDG 172
PICATINNY ARSENAL NJ
07806-5000

1 CDR USA ATCOM
AVIATION APPLIED TECH DIR
J SCHUCK
FT EUSTIS VA

1 CDR USARDEC
AMSTA AR SRE D YEE
PICATINNY ARSENAL NJ
07806-5000

NO. OF
COPIES ORGANIZATION

7 CDR USARDEC
AMSTA AR CCH B
B KONRAD
E RIVERA
G EUSTICE
S PATEL
G WAGNECZ
R SAYER
F CHANG
BLDG 65
PICATINNY ARSENAL NJ
07806-5000

1 CDR USARDEC
AMSTA AR QAC T D RIGOGLIOSO
BLDG 354 M829E3 IPT
PICATINNY ARSENAL NJ
07806-5000

ABERDEEN PROVING GROUND

73 DIR USARL
AMSRL CI
AMSRL CI C
W STUREK
AMSRL CI CB
R KASTE
AMSRL CI S
A MARK
AMSRL SL B
AMSRL SL BA
AMSRL SL BL
D BELY
AMSRL SL I
AMSRL WM
A HORST
E SCHMIDT
D VIECHNICK
G HAGNAUER
J MCCAULEY
AMSRL WM BE
G WREN
C LEVERITT
D KOOKER

NO. OF
COPIES ORGANIZATION

AMSRL WM BD
P PLOSTINS
D LYON
J NEWILL
S WILKERSON
R FIFER
B FORCH
R PESCE-RODRIGUEZ
B RICE
AMSRL WM MA
R SHUFORD
S MCKNIGHT
AMSRL WM MB
B BURNS
W DRYSDALE
J BENDER
L BURTON
D HOPKINS
C HOPPEL
D HENRY
R KASTE
G GAZONAS
M LEADORE
R LIEB
J TZENG
T BLANAS
T BOGETTI
P DEHMER
R DOOLEY
B FINK
S GHIORSE
D GRANVILLE
E RIGAS
D SPAGNUOLO
W SPURGEON
R BOSSOLI
S CORNELISON
A ABRAHAMIAN
M BERMAN
A FRYDMAN
T LI
W MCINTOSH
E SZYMANSKI
AMSRL WM MC
J BEATTY
AMSRL WM MD
W ROY
AMSRL WM T
D DIETRICH

NO. OF
COPIES ORGANIZATION

AMSRL WM TA
W GILLICH
E RAPACKI
T HAVEL
AMSRL WM TC
R COATES
W DE ROSSET
AMSRL WM TD
W BRUCHEY
A DAS GUPTA
AMSRL WM BB
H ROGERS
AMSRL WM BA
F BRANDON
W D AMICO
AMSRL WM BR
J BORNSTEIN
AMSRL WM TE
A NIILER
AMSRL WM BF
J LACETERA

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE July 1999	3. REPORT TYPE AND DATES COVERED Final, May 98 - 99		
4. TITLE AND SUBTITLE Theoretical Evaluation of Moisture Protection Using Coatings		5. FUNDING NUMBERS 1L162622AH3		
6. AUTHOR(S) J. F. Newill, S. H. McKnight, C. P. R. Hoppel, G. R. Cooper, and M. S. Berman				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-BC Aberdeen Proving Ground, MD 21005-5066		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-2016		
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.		12b. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words) A theoretical approach is used to determine important attributes for moisture protection of polymer-matrix composite structures provided by polymeric coatings. Developed solutions are used to evaluate a range of coating materials and thicknesses for thin and thick substrates. The diffusion constants and the saturation levels for the coating material were obtained from the range of available coating materials. The results include typical diffusion patterns for coating materials, saturation of the coating layer, development of moisture through time, and effects of the material properties for the various substrate thicknesses. Moisture diffusion behavior at the substrate-coating interface is also presented. For relatively thick coating layers, the results show that the diffusion constant and the saturation level of the coating must both be low to significantly affect the diffusion process. The study also shows differences in the behavior of the substrate-coating interface.				
14. SUBJECT TERMS barrier coatings, moisture diffusion, composites		15. NUMBER OF PAGES 37		
		16. PRICE CODE		
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-2016 (Newill) Date of Report June 1999

2. Date Report Received _____

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)